

## EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	28039	((amorphous glassy) (glass and (alloy metal))).clm.	US-PGPUB	OR	ON	2007/03/13 09:58
L2	1265	((((silicon Si) same (B boron) same (Co cobalt)) and (Fe iron Zr zirconium Nb niobium Ta tantalum Hf hafnium Mo molybdenum Ti titanium vanadium Cr chromium Pd palladium W tungsten))).clm.	US-PGPUB	OR	ON	2007/03/13 09:58
L3	251	1 and 2	US-PGPUB	OR	ON	2007/03/13 09:58
L4	4862	((glass adj2 transition) adj2 temperature).clm.	US-PGPUB	OR	ON	2007/03/13 09:59
L5	8	1 and 2 and 4	US-PGPUB	OR	ON	2007/03/13 09:59
L6	3	(supercooled adj5 interval).clm.	US-PGPUB	OR	ON	2007/03/13 09:59
L7	59	(supercooled adj5 liquid).clm.	US-PGPUB	OR	ON	2007/03/13 10:00
L8	184840	(thick thickness diameter).clm.	US-PGPUB	OR	ON	2007/03/13 10:00
L9	129	1 and 2 and 8	US-PGPUB	OR	ON	2007/03/13 10:01
L10	3	1 and 2 and 8 and 4	US-PGPUB	OR	ON	2007/03/13 10:01
L11	1029	((Co cobalt) adj3 (base based)).clm.	US-PGPUB	OR	ON	2007/03/13 10:02
L12	0	(supercooled adj2 interval).clm.	US-PGPUB	OR	ON	2007/03/13 10:02